



AS 420 M2

1	WIDTH	NF EN 1773	120 ou 180 cm	+ or - 1
2	BASE FABRIC	nature	Polyester 280 dtex HT	
		weight	130 g/m ²	
3	COATING	nature	2 PVC faces	
		weight	270 g/m ²	
4	FINISH		bouchonné	
5	TOTAL WEIGHT	NF EN ISO 2286-2	400 g/m ²	+ or - 20
6	Trapezoidal TEAR POINT warp/weft	NF EN 1875-3	15 / 12 daN	*
7	TENSILE STRENGTH warp/weft	NF EN ISO 1421	190 / 160 daN	* / **
8	FLAME RETARDANCY	NF P 92 503	M2	
9	COLD	NF EN 1876-2	- 20 °C	

* Average values from laboratory tests

** /5 cm

MS 07/06

